

## Rustblock Heavy Duty Metal Primer

### Production Description

Omega Rustblock Heavy Duty Metal Primer is a high performance, anti-corrosive metal primer. Rustblock Heavy Duty Metal Primer forms a tough, flexible anti-corrosive coating to resist corrosion, even in the harshest of environments. Rustblock Heavy Duty Metal Primer provides outstanding rust protection and is an excellent base for Rustblock Epoxy Gloss Enamel and other quality Omega top coat finishes

### Areas of Application

Exterior and Interior applications. Ideal for use on zincalume® and galvanised Iron, for priming steel, wrought iron and structural steel  
For use on roofs, wrought iron railings, gutters, down pipes and general structural steel work.

### Technical Data

|                                  |  |
|----------------------------------|--|
| Colour                           | White, Grey and tinted colours                             |
| Solvent Resistance               | Good   |
| Toxicity                         | Dry film is not toxic                                      |
| Thinning & Clean Up              | Omega Enamel Thinner. Up to 10% thinner for spraying       |
| Theoretical Coverage*            | 8 - 10 sq.m. / litre depends on surface profile            |
| Drying Time (at 25 C & RH 60%)** | Touch dry 1 hours ** / Recoat: 8 hours**                   |
| Sheen Level                      | Matt   |
| Packs available                  | 1 litre, 4 litre, 300g Spray Pack (other sizes on request) |

\*Practical coverage depends on surface profile, method of application and dry film thickness. Higher film thickness leads to lower coverage.

\*\* Cooler temperature, higher film thickness, or higher humidity conditions will lead to longer drying times.

### Method of Application

Can be applied by brush, roller or spray. Please use the method best suited to your requirement and skill..

### Surface Preparation

Remove all surface rust, loose and flaking / peeling paint and sand back coating edges. Ensure surface is clean, dry and free from dust, grease, oil and all other surface contamination. Apply Omega Rustblock Rust Converter to rusted surfaces. Prepare and coat section by section to achieve best results Surface is to be coated immediately after preparation.

Note: Cooler temperature, higher film thickness, or higher humidity conditions will lead to longer drying times Do not apply when surface temperature is below 10<sup>0</sup> C or above 35<sup>0</sup> C

### Application

Stir contents thoroughly using a flat stirrer before and during use. Apply one coat evenly by brush, roller or spray, after proper surface preparation. Avoid over-brushing and rolling. For brush or roller application do not use more than 3% with Omega Enamel Thinner. If spraying, thin up to 10% with Omega Enamel Thinner. Allow Rustblock Heavy Duty Metal Primer to dry for at least 8 hours before application of finishing product. Note: For best results, prepare, prime and finish section by section to avoid prolonged exposure to the elements.

## Rustblock Heavy Duty Metal Primer

### Mix and Colour Check

Mix the paint before application with a wide flat (25mm) paddle or a hand paint mixer with a perforated base, in a circular lifting motion from the bottom of the container for 5 minutes or until the paint and colour are thoroughly mixed. Remix the paint every 2 hours to ensure product consistency.

Check colour to the colour chart/standard prior to application. Inner mix multiple containers together to ensure colour consistency. Replace and secure container lid during painting to prevent the paint drying within the container.

### Flammability & Transport

- Highly flammable, Dangerous Goods Class 3.2, Flash Point 32<sup>0</sup> C, UN 1263, PG III
- Keep away from heat and flame, eliminate any source of ignition.
- Soak all used cloths and rags immediately in water to prevent self-ignition.
- Ensure container is upright with lid secure.
- Ensure the container is secured in the vehicle for transport.

### Environmental

- Do not wash painting equipment and allow waste to enter drains and water ways.
- Do not dispose of unwanted paint and thinners that will enter drains and water ways.
- Refer to state / local EPA and council web sites for environmental and safe disposal details.

### Safety & Precautions

- Do not apply when surface temperature is below 10<sup>0</sup> C or over 35<sup>0</sup> C
- Do not apply in environments of high humidity/moisture, or if pending rain is a possibility.
- Apply in calm fine weather conditions and only during daylight hours.
- Cease painting 2 hours before sunset or if weather changes are forecast.
- Use only the recommended thinner for dilution and cleaning.
- Check paint colour to the colour chart/standard prior to application
- Provide adequate ventilation during use.
- Keep out of reach of children
- Avoid exposure of the new paint film to steam for 48 hours and to washing or scrubbing for 7 days.
- Check cross cut adhesion test of old coating before repainting.
- **Apply a test sample for compatibility of this product over a small test area.**

The technical information and suggestions for use and application are given in good faith. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise. The manufacturer does not assume any liability for any loss or injury resulting from the use of the product. Cooler temperature, higher film thickness and higher humidity conditions will require longer drying times

Omega Paints Pty Ltd., 111 Kurrajong Avenue Mt Druitt NSW 2770 Phone (02) 9832 0000 /

info@omegapaints.com.au

Reviewed Sep 2017