

## Mineral Turpentine Thinner

### Production Description

Mineral turpentine is a slow-evaporating cost effective solvent with good solvency for aromatic and aliphatic alkyd based system and can be used as both thinner and cleaning solvent. It is especially recommended when a longer open time is desired for better levelling.

### Areas of Application

Recommended to be used as thinner or clean-up solvent for alkyd based primers and gloss enamel.

### Technical Data

Appearance	Low viscosity, colourless clear liquid
Specific Gravity	0.82
Boiling Range	146-197 °C
Thinning Recommendations	Spray application: up to 20% as required, depending on product. Dipping application: up to 50% as required
Packs available	1 litre, 4 litre, 20 litre, 60 litre & 200 litre

### Flammability & Transport

- Highly flammable, Dangerous Goods Class 3.2.
- Keep away from heat and flame, eliminate any source of ignition.
- Soak all used cloths and rags immediately in water to prevent self-ignition.
- Ensure container is upright with lid secure.
- Ensure the container is secured in the vehicle for transport.

### Safety & Precautions

Refer to SDS for detail instructions.

The technical information and suggestions for use and application are given in good faith. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise. The manufacturer does not assume any liability for any loss or injury resulting from the use of the product. Cooler temperature, higher film thickness and higher humidity conditions will require longer drying times

**Omega Paints Pty Ltd**  
111 Kurrajong Avenue, Mount Druitt NSW 2770  
t. (02) 9832 5900 | f. (02) 9677 0566  
www.omegapaints.com.au  
Date of Revision: July 2014