

Anti-Rust Primer

Production Description

A premium quality alkyd based zinc phosphate primer formulated for all ferrous metals. The primer has very good anticorrosive properties and excellent adhesion to metal surfaces.

Areas of Application

All common metal surfaces except Zinc, Galvanised Iron and Aluminium. Can also be used for coating on automotive chassis For interior and exterior applications.

Technical Data

Colour Range	Red and Grey Oxide
Gloss Level at 60° head	Flat
Solvent Resistance	Resistance to aliphatic hydrocarbons is good. Polar solvents & chlorinated solvents are liable to attack the film.
Toxicity	Dry film is not toxic
Thinning & Clean Up	Enamel Thinner 600 / Min turps. Though product is designed for undiluted application, up to 10% thinner can be used if necessary.
Thinning Rate	Up to 5% thinner may be necessary depending on method of application and climatic conditions.
Theoretical Coverage**	14 sq. m. / litre per coat. Practical coverage may depend on surface profile, method of application and losses.
Drying Time (at 25C & RH 60%)*	Touch Dry 4 hours / Recoat 24 hours*
Packs available	1 litre, 4 litre,

*Cooler temperature, higher film thickness and higher humidity conditions will require longer drying times

**Practical coverage may depend on surface profile, method of application and losses. Higher film thickness will lead to lower coverage.

Method of Application

Brush, Roller or Spray. Please use the method best suited to your requirement and skill. Use of a synthetic or mohair sleeve of 5 mm nap is suggested on flat surfaces. For airless spray application, optimum pressure of 2200 psi and nozzle size of 0.011-0.013 inches is suggested as a guideline.

Surface Preparation

Remove all surface rust, loose and flaking / peeling paint and sand back coating edges. Ensure surface is clean, dry and free from dust, grease, oil and all other surface contamination. Sand previously painted surfaces thoroughly to provide a key for adhesion. Check cross cut adhesion test of old coating before recoating Apply Omega Rustblock Rust Converter to rusted surfaces. Spot prime bare surfaces with Rustblock Primer. Prepare and coat section by section to achieve best results Surface is to be coated immediately after preparation. On old galvanised iron and aluminium surfaces apply one coat of Omega Rustblock Etch primer. On new Galvanised Iron Galvanised Iron Primer can be used.

Note: Cooler temperature, higher film thickness, or higher humidity conditions will lead to longer drying times. Do not apply when surface temperature is below 100 C or above 350 C. Avoid painting in high humidity and moisture as this will affect the finished gloss level.

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apccoatings.com.au
www.apccoatings.com.au

Anti-Rust Primer

Mix and Colour Check

Mix the paint before application with a wide flat (25mm) paddle or a hand paint mixer with a perforated base, in a circular lifting motion from the bottom of the container for 5 minutes or until the paint and colour are thoroughly mixed. Remix the paint every 2 hours to ensure product consistency. Check colour to the colour chart/standard prior to application. Inner mix multiple containers together to ensure colour consistency. Replace and secure container lid during painting to prevent the paint drying within the container.

Coating Maintenance

Washing the painted surface periodically will maintain the look of a newly painted surface longer. Clean the surface with a diluted sugar soap or a mild detergent and rinse well with clean water. Do not use scouring pads, abrasive brushes, high pressure washing or solvent to clean the painted surface. These will damage the paint film and cause premature failure of the coating.

Flammability & Transport

- Highly flammable, Dangerous Goods Class 3.2, Flash Point 32⁰ C, UN 1263, PG III
- Keep away from heat and flame, eliminate any source of ignition.
- Soak all used cloths and rags immediately in water to prevent self-ignition.
- Ensure container is upright with lid secure.
- Ensure the container is secured in the vehicle for transport.

Environmental

- Do not wash painting equipment and allow waste to enter drains and water ways.
- Do not dispose of unwanted paint and thinners that will enter drains and water ways.
- Refer to state / local EPA and council web sites for environmental and safe disposal details.

Safety & Precautions

- Do not apply when surface temperature is below 10⁰ C or over 35⁰ C
- Do not apply in environments of high humidity/moisture, or if pending rain is a possibility.
- Apply in calm fine weather conditions and only during daylight hours.
- Cease painting 2 hours before sunset or if weather changes are forecast.
- Use only the recommended thinner for dilution and cleaning.
- Check paint colour to the colour chart/standard prior to application
- Provide adequate ventilation during use.
- Keep out of reach of children
- Avoid exposure of the new paint film to steam for 48 hours and to washing or scrubbing for 7 days.
- Check cross cut adhesion test of old coating before repainting.
- Apply a test sample for compatibility of this product over a small test area.

The technical information and suggestions for use and application are given in good faith. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise. The manufacturer does not assume any liability for any loss or injury resulting from the use of the product. Cooler temperature, higher film thickness and higher humidity conditions will require longer drying times.

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apccoatings.com.au
www.apccoatings.com.au



APCO Coatings
13-27, Melboure Road, Riverstone NSW 2765 Phone (02) 9832 0000 / info@apcocoatings.com.au
Reviewed June 2019

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apcocoatings.com.au
www.apcocoatings.com.au